




Name	Color	Approximative color codes (satin glass)			Performance Retained (%)
		RAL Classic	RAL Design	NCS 1950	
White				1005-R80B	55%
Light Grey			260 80 05		75%
Dark Grey				6005-R80B	90%
Terracotta		8002		6020-Y50R	82%
Dark Brown			040 30 10		88%
Grey-Beige				4005-G80Y	80%
Barbados Beige			090 70 10	3005-Y20R	70%
Light Terracotta				4010 Y50R	71%
Pine Green		6028	160 40 20		80%
Verdigris			160 70 10		61%
Ocean Blue			220 50 15		72%
Falu Red		3009		5040-Y80R	64%
Terra Orange			040 60 40	3040 Y 80R	53%
Gold					72%

The above information is based on tests or experience which Solaxess believes to be reliable, but the accuracy or completeness of such information is not guaranteed.

Due to the variety of factors that can affect the use and performance of a Solaxess product, it is the PV module manufacturer responsibility to conduct its own testing with its known components (encapsulants, glass type, cell type, etc.) to ensure color rendition and performance for the targeted application.

For custom color enquiries, please contact us at info@solaxess.ch.